

Diametro mm	Peso c.a. Kg/m	Carico di rottura min. in Kg con fili di resistenza min. 150 Kg/mm ²	Sez. metallica tot. mm ²
		180	
4	0.065	1040	7.05
5	0.1	1500	10.6
6	0.15	2400	16.7
7	0.2	3200	22
8	0.265	3800	26.1
9	0.33	5500	37.6
10	0.39	6450	44.1
11	0.45	7500	51.1
12	0.59	9800	66.8
13	0.66	11000	75.4
14	0.77	12400	84.6
15	0.92	15300	104
16	1.02	16900	115
18	1.32	22100	150
20	1.55	25900	176